

RUBBER SPONGE Data links

Type	Item	Density (g/cm ³)	Hardness (AskerC)	25% Compression (kPa)	Set	Block Size (mm)	Slice Thickness (mm)	Specification Sheet	Compression Defective Curve (0~80%)	Safety Data Sheet SDS	RoHS Analysis	Notes
N R	N-149	0, 100±0.03	8±5	19.6~49.0		30 x 1000 x 1000	1.5 ~ 28	Q	Q	Q	Q	
	N-138	0, 150±0.03	15±5	34.3~63.7		25 x 1000 x 1300	1 ~ 23	Q	Q	Q	Q	
	N-148	0, 150±0.03	15±5	34.3~63.7		25 x 1000 x 1300	1 ~ 23	Q	Q	Q	Q	
	N-145	0, 180±0.03	20±5	39.2~68.6		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
						30 x 1000 x 1500	1 ~ 28					
	N-146	0, 150±0.03	30±5	68.6~98.1		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
						25 x 1000 x 1300	1 ~ 23					
C R	N-147	0, 170±0.03	33±5	73.5~112.8		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
	C-4205	0, 180±0.03	10±5	29.4~58.8		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed
	C-4215	0, 180±0.03	15±5	34.3~63.7		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 Equivalent
	C-4305	0, 190±0.03	25±5	61.9~93.2		30 x 1000 x 1000	0.5 ~ 28	Q	Q	Q	Q	UL94HF-1 passed
						35 x 1000 x 1000	1 ~ 33					
						30 x 1000 x 1300	1 ~ 28					
						30 x 1000 x 2000	1 ~ 28					
	C-4405	0, 200±0.03	25±5	53.9~83.4		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed
	C-4505	0, 250±0.03	35±5	88.3~127.5		20 x 1000 x 1000	1 ~ 18	Q	Q	Q	Q	
	C-4500	0, 250±0.03	40±5	103.0~205.9		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
	C-4555	0, 250±0.03	50±5	137.3~205.9		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
	C-4600	0, 300±0.04	50±5	137.3~215.7		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
	C-4315	0, 190±0.03	20±5	29.4~68.6		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed Gray
	C-4316	0, 190±0.03	20±5	29.4~68.4		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 Equivalent Blue
	C-4266	0, 200±0.03	22±5	49.0~88.3		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed Low Sulfur
	CD-4312	0, 180±0.03	25±5	44.1~73.5		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed Low Odor
E P D M	E-4070	0, 100±0.03	5±3	9.8~39.2		33 x 1000 x 1300	1 ~ 30	Q	Q	Q	Q	
	E-4088	0, 100±0.03	7±5	14.7~44.1		33 x 1000 x 1300 30 x 1000 x 2000	1 ~ 30 1.5 ~ 28	Q	Q	Q	Q	
	E-4188	0, 120±0.03	10±5	14.7~44.1		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
	E-4288B	0, 120±0.03	12±5	19.6~63.7		30 x 1000 x 1500	1 ~ 28	Q	Q	Q	Q	
	E-4388B	0, 150±0.03	20±5	39.2~78.4		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
						30 x 1000 x 1300	1 ~ 28					
	E-4408B	0, 240±0.04	35±5	88.3~166.7		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
	E-4108	0, 150±0.03	15±5	29.4~58.8		30 x 1000 x 1000	1.5 ~ 28	Q	Q	Q	Q	Gray
	E-4390	0, 170±0.03	20±5	39.2~78.4		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	White
	E-4490	0, 220±0.04	30±5	60.0~120.0		25 x 1000 x 1000	1 ~ 23	Q	Q	Q	Q	Gray
	E-4385	0, 120±0.03	25±5	39.2~78.4		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	Conductive
	E-4238	0, 150±0.03	10±5	19.6~63.7		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed Low Sulfur
	E-4338	0, 150±0.03	20±5	39.2~78.4		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed Low Sulfur
	E-4301	0, 150±0.03	18±5	35.1~65.0		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	UL94HF-1 passed Low VOC
N B R	NBR-4112E	0, 150±0.03	15±5	34.3~63.7		30 x 1000 x 1000	1 ~ 28	Q	Q	Q	Q	
S I	TT-4101	0, 250±0.05	10±5	14.7~63.7		22 x 500 x 500	1.5 ~ 22	Q	Q	Q	Q	Orange
						22 x 500 x 1000	2 ~ 22					
	TT-4102	0, 250±0.05	10±5	14.7~63.7		22 x 500 x 500	1.5 ~ 22	Q	Q	Q	Q	Gray
						22 x 500 x 1000	2 ~ 22					
	TT-4103	0, 250±0.05	15±5	24.5~83.4		25 x 500 x 500 25 x 500 x 1000	1 ~ 25 2 ~ 25	Q	Q	Q	Q	Black
	TT-4106	0, 250±0.05	12±5	24.5~83.4		25 x 500 x 1000	1.5 ~ 25	Q	Q	Q	Q	Black

Data that concerns quality assurance

Item	Link
Rubber sponge appearance determined standard	Q
Rubber sponge slice processing dimensional tolerance standard	Q