

### 1. Characteristics

This product is a chloroprene rubber sponge, which is a black low-hardness rubber sponge.

### 2. Product specification

#### Block

Item	Thickness (mm)	Width (mm)	Length (mm)
GOMSPOR <sup>®</sup> C-4215	30	1000	1000

#### Sliced seet

Item	Thickness (mm)	Width (mm)	Length (mm)
GOMSPOR <sup>®</sup> C-4215	1 to 28	1000	1000

### 3. Standard Physical Property

Physical Properties	Unit	Result	Specificaton	Test Method
Hardness	Type C	18	15 ± 5	JIS K7312
Tensile Strength	MPa	0.51	min 0.39	JIS K6767
Elongation	%	220	min 150	JIS K6767
Apparent Density	g/cm <sup>3</sup>	0.17	0.18 ± 0.03	JIS K6767
25% Compressed Load	kPa	52.3	34.3 to 63.7	INOAC Method

### 4. Flammability

UL94

1.0mm HF-1 equivalent

-The figures all indicate representative values.

-Test method is based on Inoac's "Physical Testing Standard for Closed-Cell Rubber Sponge".