

TYPICAL PROPERTIES of RP-300FRND

		UNIT	DATA	TEST METHOD
Density		kg/m ³ pcf	42.0 2.6	ASTM D3575 SuffixW
Compression Deflection		kPa psi	6.2 0.90	ASTM D3575 SuffixD
Compression set		%	2.3	ASTM D3575 SuffixB
Tensile strength		MPa psi	0.16 23.2	ASTM D3575 SuffixT
Tensile elongation		%	180	ASTM D3575 SuffixT
Thermal stability	LENGTH	%	-0.9	ASTM D3575 SuffixS
	WIDTH		-0.6	ASTM D3575 SuffixS
	THICKNESS		1.7	ASTM D3575 SuffixS
Flammability In-company examination			2.0~10mm	UL94 HF-1