

TYPICAL PROPERTIES of L3000

		UNIT	DATA	TEST METHOD
Density		kg/m ³ pcf	33.0 2.1	ASTM D3575 SuffixW
Compression Deflection		kPa psi	42.5 6.16	ASTM D3575 SuffixD
Compressin set		%	21,6	ASTM D3575 SuffixB
Tensile strength		MPa psi	0.25 36.3	ASTM D3575 SuffixT
Tensile elongation		%	110	ASTM D3575 SuffixT
Thermal stability	LENGTH	%	-0.3	ASTM D3575 SuffixS
	WIDTH		-0.9	ASTM D3575 SuffixS
	THICKNESS		0.3	ASTM D3575 SuffixS